



## EUCO QWIKstitch

# CHEMICAL RESISTANCE

EXCELLENT RESISTANCE	GOOD RESISTANCE	POOR RESISTANCE
Ammonium Hydroxide - 10% Solution	Acetic Acid - 20% Solution	Calcium Hypochlorite - 5%
Barium Hydroxide	Ammonium Hydroxide	Chromic Acid
Borax Solutions	Anylacetate	Ethyl Acetate
Boric Acid Solutions	Butylacetate	Formaldehyde - 37%
Brine Solution	Chlorobenzene	Formic Acid
Calcium Bisulfite Solutions	Diesel Fuel	Hydrochloric Acid - 37%
Calcium Chloride	Diethylene Glycol	Methyl Chloride
Calcium Hydroxide	Ethylene Glycol - 100%	Methyl Ethyl Keytone
Mineral Oil	Fuel Oil	Methyl Pyrrolidone
Motor Oil	Gasoline	Nitric Acid - 10%
Phosphoric Acid < 75%	Hydraulic Oils	Sodium Hydroxide - 47%
Sea Water	Linseed Oil	Sodium Hypochlorite - 5%
Soap	Lubricating Oils	Sulfuric Acid
Water	Naptha	Toluene
	Ozone	Trichlorethylene
	Potassium Hydroxide	Xyelene
	Sodium Hydroxide - 20%	
	Soybean Oil	
	Tung Oil	

This chart represents an expectation of the general effects of various chemicals, and the data should only be used as a guide. It is advisable to test the material under actual use conditions or, at minimum, simulated service conditions before specification or use.