



## CHEMICAL RESISTANCE CHART

## EUCOTHANE

## KEY

A	Not Recommended
B	Short Term Exposure/Splash & Spill ONLY
C	Long Term Exposure/Splash & Spill ONLY
D	Short Term Immersion Acceptable
E	Long Term Immersion Acceptable

CHEMICAL	RESULTS
Acetic Acid 5%	C
Acetic Acid 10%	B
Acetone	B
Ammonia	D
Brake Fluid	C
Ethyl Alcohol	D
Hydrochloric Acid 10%	D
Hydrochloric Acid 36%	C
Methylene Chloride	A
Methyl Ethyl Ketone (MEK)	B
Nitric Acid 5%	D
Nitric Acid 30%	C
Phosphoric Acid 40%	D
Sulfuric Acid 10%	D
Sulfuric Acid 30%	C
Sulfuric Acid 98%	A
Sodium Hydroxide 10%	E
Sodium Hydroxide 50%	D
Skydrol	D
Trichloroethylene	C
Distilled Water	E
Xylene	D

This data should only be used as a guide. It is advisable to test the material under actual use conditions or, at minimum, simulated service conditions before specification or use.