



INCRETE PRO-PAVER PAVER SEALER

CLEAR, NON-YELLOWING CURE & SEAL FOR INTERLOCKING PAVERS **EUCLID CHEMICAL**

PACKAGING

5 gal (18.9 L) pails and 55 gal (208 L) drums

YIELD

First coat: 100-150 ft²/gal
(2.5-3.7 m²/L)

Second coat: 150-200 ft²/gal
(3.7-5 m²/L)

APPEARANCE

Clear liquid

CLEAN UP

Tools and equipment may be cleaned with INCRETE SOLV-KLEEN, Euclid Chemical's EUCCO SOLVENT, or xylene/xylol. Run cleaning solvent through spray equipment to remove residual materials and to prevent clogging of the nozzle for future use.

SHELF LIFE

3 years in original, unopened container

SPECIFICATIONS AND COMPLIANCES

ASTM C 1315, Type 1, Class A
ASTM C 309, Type 1, Class A & B

BRIEF OVERVIEW

INCRETE PRO-PAVER PAVER SEALER is a clear sealer formulated with pure acrylic resins. INCRETE PRO-PAVER PAVER SEALER is non-yellowing and is highly recommended for exterior use. Its solvent based formula provides lasting protection. INCRETE PRO-PAVER PAVER SEALER will darken and highlight the color of pavers, roof tiles, and other concrete products; giving these materials a rich, "wet" look.

PRODUCT CHARACTERISTICS

ADVANTAGES

- Excellent cure and durable seal
- Non-yellowing formula
- Perfect for interior or exterior
- Revives color
- Makes pavers water and stain resistant
- Makes surface easy to clean

COMMON USES

- Concrete pavers

- Concrete roof tiles
- Integrally-colored concrete
- Stamped Concrete
- Acid-stained concrete
- Decorative concrete overlays
- Porous natural stone

COMMON APPLICATION METHODS

- Sprayer
- Roller

TECHNICAL INFORMATION

The following results were developed under laboratory conditions.

Drying time* at 73 °F (22.7 °C), 50% RH:	<1 hour
Recoat	4 to 24 hours
Foot traffic	4 to 6 hours
Wheel traffic	6 to 10 hours
VOC content	681 g/L
Adhesion to concrete.....	excellent
Alkali resistance 48-hour exposure	excellent
Solvent resistance	minimal
Resistance to yellowing from UV exposure	excellent
Solids content.....	>25%
Moisture loss (ASTM C 156)	<0.40 kg/m ²

**Low concrete or air temperature and/or high relative humidity will extend drying time.*

DIRECTIONS FOR USE

SURFACE PREPARATION

The paver surface must be clean and dry. INCRETE PRO-PAVER PAVER SEALER should not be applied over other coatings. Use INCRETE UNI-STRIPP to remove old coatings. All old paint, oil, grease and water-based sealers must be removed. INCRETE JET PHOS can be used to remove any rust stains or efflorescence. Older pavers should be cleaned with a cleaner/degreaser specifically designed for concrete and paver surfaces.

APPLICATION

INCRETE PRO-PAVER PAVER SEALER requires no pre-mixing and should be used directly from the container. Apply at a uniform coverage rate with an industrial, hand-held, pump-up or airless sprayer, or by roller. Plastic garden-type sprayers should not be used. If applying by roller, use a short, 3/8 in (9.5 mm) nap, solvent-resistant roller cover. Allow the first coat to dry tack-free before applying the second coat. Best performance and appearance is achieved with two coats, following the recommended coverage rates. For a slip-resistant surface, add INCRETE SHUR GRIP to the final coat of sealer. If a low-gloss finish is desired, use INCRETE MATTE ADD per directions. Thick applications of INCRETE PRO-PAVER PAVER SEALER, too many successive coats, or multiple coats over time can cause bubbling, whitening, peeling, and ultimate failure of the product. To prevent over-application, it is good practice to measure the area to be sealed and the corresponding volume of product required based on the coverage rate. Also, applying INCRETE PRO-PAVER PAVER SEALER in hot weather or onto a hot surface can cause bubbling. If INCRETE PRO-PAVER PAVER SEALER is showing signs of over-application, scrub the surface with a solvent such as INCRETE SOLV-KLEEN or xylene using a stiff, natural-bristle brush. Keep the surface wet with the solvent while scrubbing, adding more if necessary. The solvent will turn the sealer back into a liquid form, at which point excess material can be wiped off with a lint-free mop or towel. Do not apply additional sealer. After removing the excess INCRETE PRO-PAVER PAVER SEALER, a roller can be used to redistribute the remaining product evenly across the surface, adding more solvent as necessary to keep the sealer wet.

MAINTENANCE

Clean, as needed, with a cleaner/degreaser specifically designed for concrete and paver surfaces. Rinse after cleaning. If the surface begins to dull due to extensive use (typically 3-4 years), an additional coat of INCRETE PRO-PAVER PAVER SEALER will restore the original luster. A light maintenance coat is recommended every 1 to 2 years depending on the surface exposure to traffic, abrasion, weathering, etc.

PRECAUTIONS/LIMITATIONS

- Use with adequate ventilation. Keep away from all sources of ignition. If solvent odor is objectionable, use a water-based, low-odor product.
- Material will not freeze in storage but should be allowed to rise to 50 °F (10 °C) or more before use.
- Do not apply when concrete surfaces or ambient temperatures are below 40 °F (4 °C), or if rain is expected within 12 hours after application. Application in hot, direct sunlight or when concrete or air temperatures are >95 °F (35 °C) can cause bubbling.
- Excessive build-up of INCRETE PRO-PAVER PAVER SEALER or allowing product to puddle during application can lead to bubbling and discoloration.
- Do not thin.
- Do not apply over curing compounds. Complete removal is necessary before applying INCRETE PRO-PAVER PAVER SEALER
- Not resistant to gasoline or other automotive fluids.
- For professional use only.
- In all cases, consult the Safety Data Sheet before use.

Rev. 07.21

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.