



# DIAMOND-PLATE LIGHT REFLECTIVE

## NON-OXIDIZING, LIGHT REFLECTIVE, METALLIC FLOOR HARDENER

### PACKAGING

50 lb (22.7 kg) bag  
Code: 162B 50

### APPROXIMATE COVERAGE

DIAMOND-PLATE LIGHT REFLECTIVE may be applied at rates from 1.0 to 3.0 lb/ft<sup>2</sup> (4.9 to 14.6 kg/m<sup>2</sup>). Greater application rates yield better total abrasion resistance and may be used with special considerations. Contact your Euclid Chemical Company representative for recommended procedures.

### CLEAN UP

Clean tools and equipment with water before the material hardens.

### SHELF LIFE

2 years in original, unopened package

### SPECIFICATIONS AND COMPLIANCES

- Canadian Food Inspection Agency compliant

### DESCRIPTION

DIAMOND-PLATE LIGHT REFLECTIVE is a metallic, dry shake floor hardener with graded, non-oxidizing metallic aggregate in a high strength cementitious binder. Designed to be incorporated into fresh concrete slabs, DIAMOND-PLATE LIGHT REFLECTIVE provides a dense, tough surface capable of withstanding the abrasion and impact loading seen by floor slabs of numerous industrial and manufacturing facilities. DIAMOND-PLATE LIGHT REFLECTIVE has been specially formulated to give increased reflectivity and to improve lighting levels in combination with a non-rusting aggregate for increased abrasion resistance. DIAMOND-PLATE LIGHT REFLECTIVE can also be mixed into a mortar consistency and placed along joints to provide edge reinforcement.

### PRODUCT CHARACTERISTICS

#### FEATURES/BENEFITS

- Provides a high strength wearing surface in areas subject to constant or frequently wet conditions without oxidizing
- Metallic aggregate is free of rust, oil, or other contaminants
- Virtually non-dusting in service, easy to clean and maintain
- Capable of reducing annual energy costs with lowering of electrical requirements due to improved lighting
- Can be applied at coverage rates up to 3.0 lb/ft<sup>2</sup> (14.6 kg/m<sup>2</sup>)

#### PRIMARY APPLICATIONS

- Industrial floors
- Loading docks
- Warehouses
- Main, high traffic aisleways
- Processing plants
- Passenger and freight terminals
- Towveyors
- Distribution centers
- Joint shoulder reinforcement

#### APPEARANCE

DIAMOND-PLATE LIGHT REFLECTIVE is a free flowing powder as packaged. The color will appear darker after placement on the concrete surface, but will lighten substantially after curing. The final finish can be any texture normally achieved with concrete and should be specified by the owner.

### TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109	Compressive Strength	2 in. (50 mm) cubes, mixed at 4.50 lb (2.04 kg) of water per 50 lb (22.7 kg) bag 7 days . . . . .11,000 psi (75.9 MPa) 28 days . . . . .13,000 psi (89.7 MPa)
ASTM C779	Relative Abrasion Resistance	Abrasion @ 30 min.      Abrasion @ 60 min 7 days . . . . . 0.013" (0.33 mm). . . . . 0.038" (0.97 mm) 28 days. . . . . 0.012" (0.30 mm). . . . . 0.034" (0.86 mm)

---

## DIRECTIONS FOR USE

The contractor and engineer are encouraged to consult and review the Euclid Chemical bulletin **“Dry Shake Floor Hardeners - Application Instructions”**. The document offers instructions detailing the general installation of Euclid Chemical manufactured dry shake floor hardeners. **Note:** *If the contractor is not familiar with the standard application techniques of a dry shake floor hardener, a pre-job meeting is suggested to review the project concrete mix design as well as placement and curing details unique to the particular job. Contact your local Euclid Chemical Company representative for additional information.*

**Concrete Mix Design Note:** Concrete containing calcium chloride or admixtures with > 0.05% chloride ions should not be treated with metallic dry shakes. Air content must be below 3% for all dry shakes. Cement should be the only cementitious material present in the mix. The use of supplementary cementitious materials, such as fly ash, slag, and microsilica can cause delayed bleeding and are not recommended for use with a dry shake hardener.

**Armored Joints:** DIAMOND-PLATE LIGHT REFLECTIVE may also be used as a mortar in constructing armored floor joints.

**Application Tips:** Colored (pigmented) dry shakes require special attention for a uniform color. Care should be taken with regard to the following; delay application of the shake as long as possible to get the maximum color saturation at the surface of the slab, apply the shake as evenly as possible and in two applications for maximum uniformity. For color consistency, do not over trowel the floor.

**Curing and Sealing:** After finishing operations are complete and the surface will not be marred by foot traffic, apply a Euclid Chemical curing compound or cure and seal according to product instructions. To produce an exceptionally durable and dustproof surface, cure with a dissipating curing compound such as KUREZ DR VOX, then densify with EUCO DIAMOND HARD.

---

## PRECAUTIONS/LIMITATIONS

- The use of supplementary cementitious materials are not recommended for use with a dry shake hardener
- Proper curing and sealing is required.
- Do not cure this product with UltraSil 7 or UltraSil DC9
- Curing with a sheet membrane (poly or burlene) is acceptable, however potential mottling problems may occur.
- Sufficient labor is required to produce consistent results on large placements.
- **Important:** Air-entraining admixtures may complicate finishing operations and cause blistering. Contact The Euclid Chemical Company if the application of this product will be on air entrained concrete with more than 3% total air content.
- Do not burnish light reflective surface hardeners.
- Not recommended for floors subjected to acids or other corrosive chemicals that may attack a cement based material.
- Store product in a dry place.
- When necessary, follow the recommendations in ACI 305R “Guide to Hot Weather Concreting” or ACI 306R “Guide to Cold Weather Concreting”.
- In all cases, consult the Safety Data Sheet before use.

Rev. 08.24

---

**WARRANTY:** The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.