

## HORIZONTAL REPAIR

Master Format #: 03 01 30.61

# EUCO RE-COVER FINE

## FIBER REINFORCED CONCRETE RESURFACER



**EUCLID CHEMICAL**

### PACKAGING

40 lb (18 kg) bag

### APPROXIMATE YIELD

**40 lb (18 kg) unit:** 0.48 ft<sup>3</sup> (0.014 m<sup>3</sup>) per unit when mixed with 4.5 quarts (4.3 L) of potable water.

A mixed unit of EUCO RE-COVER FINE will cover approximately 92 ft<sup>2</sup> (8.6 m<sup>2</sup>) at 1/16" (1.6 mm).

### MINIMUM/MAXIMUM APPLICATION THICKNESS

Featheredge to 3/8 inch (10 mm)

### CLEAN UP

Clean tools and equipment with water before the material hardens.

### SHELF LIFE

2 years in original, unopened package

### DESCRIPTION

EUCO RE-COVER FINE is a polymer modified, fiber-reinforced concrete resurfacing mortar. Adding only water, EUCO RE-COVER FINE provides a fresh, aesthetically pleasing appearance to new concrete that has been marred by rain or plastic covering, old or spalled concrete, and salt damaged concrete.

### PRODUCT CHARACTERISTICS

#### FEATURES/BENEFITS

- Excellent working time at 70 °F (21 °C)
- Polymer modified
- Micro-fiber reinforced
- Suitable for freeze-thaw environments
- Open to foot traffic in 4 hours, rubber tire traffic in 12 hours at 75 °F (24 °C)

#### PRIMARY APPLICATIONS

- Driveways
- Sidewalks
- Pool decks
- Garage floors
- Elevated slabs
- Vertical concrete surfaces

### TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
-	Working Time	30 minutes at 70 °F (21 °C)
ASTM C266	Initial Set	approximately 1 hour
ASTM C266	Final Set	approximately 2.5 hours
ASTM C109	Compressive Strength	4000 psi (28 MPa) at 28 days

The following coverage rates are approximations based on yield of a 40 lb unit mixed at standard consistency.

Application Thickness (inches)	1/16	1/8	1/4	3/8
Coverage Area per Unit (ft <sup>2</sup> )	92.1	46.0	23.0	15.3

---

## DIRECTIONS FOR USE

**Surface Preparation:** Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and be free of curing and sealing compounds, dust, dirt, paint, efflorescence, oil and all other contaminants. Typically, pressure washing the surface with a commercial pressure washer (3000 psi, 4 GPM) (21MPa, 0.25 L/s) and allowing to fully dry will be sufficient for preparation. In areas of heavy contamination, preparing the concrete through mechanical means is recommended. Abrade the surface to a profile of at least CSP 2, in accordance with ICRI Guideline 310.2-1997.

**Priming:** Apply EUCO RE-COVER FINE to dry surfaces. Although a primer is typically not needed, if the concrete is very porous TAMMSWELD or EUCOWELD 2.0 bonding adhesive must be used to prevent pinholes from forming in the EUCO RE-COVER FINE. Please refer to the TAMMSWELD or EUCOWELD 2.0 technical data sheet for further instructions.

**Mixing:** One 40 lb (18 kg) unit requires 4.5 qt (4.3 L) of potable water. Up to an additional pint (0.4 L) can be added when the temperature exceeds 80 °F (27 °C). For repairing deeper spalls prior to overlaying, one unit can be mixed with 3.5 to 4 qt (3.3 to 3.8 L) of potable water to make a stiff paste suitable for spall repairs. All materials should be in the proper temperature range of 50 to 90 °F (10 to 32 °C). Single 40 lb (18 kg) units may be mixed with a drill and “jiffy” mixer. Add 80% of the total mix water to a clean mixing vessel, then gradually add the dry product. Slowly add the remaining 20% of mix water during mixing. Do not exceed maximum water or add any additional additives. Mix for 3 to 5 minutes. Do not retemper. Place immediately.

**Coloring:** EUCO RE-COVER FINE can be integrally colored. Add the desired liquid or dry colorant to the mixing water and stir until colorant evenly disperses throughout the water. Continue mixing in the EUCO RE-COVER FINE as directed. The Euclid Chemical Company does not warrant any colored application. For even results, it is a best practice to “box” all mixing water that has been colored prior to mixing individual bags of EUCO RE-COVER FINE. Colored results vary based on the colorant and amount used.

**Placement:** Ambient and surface temperatures should be at least 50 °F (10 °C). Working time at 70 °F (21 °C) is approximately 30 minutes. Surface and air temperatures greatly affect the working time of the material. Place the mixed EUCO RE-COVER Fine onto the concrete in the desired area. For best adhesion to the concrete, use a scrub brush or stiff street broom to scrub the material onto the prepared substrate. Working from joint to joint in the base concrete is a good practice. Since EUCO RE-COVER FINE is a thinly applied material, surface and air temperatures greatly effect the working time of the material. On hotter days, it is best practice to work in small, controlled areas to avoid cold joints. This product is designed for finishing with a trowel or a broom. The maximum placement depth of EUCO RE-COVER FINE is 3/8” (9.5 mm). If multiple lifts are to be applied, score the previous lift after placing to provide a suitable surface for mechanically bonding subsequent lifts. Use Euclid Chemical’s EUCOBAR evaporation retardant to retain moisture in the material and to provide longer finishing time. All saw cuts and joints in the base concrete will have to be honored through the EUCO RE-COVER FINE material.

**Curing and Sealing:** Proper curing procedures are important to ensure the durability and quality of the repair. As soon as the material can be walked on without harming the finish, apply a water-based cure and seal compound to the EUCO RE-COVER FINE. If you can apply a cure and seal sooner from the sides of the project, then do so. The use of Euclid Chemical’s DIAMOND CLEAR VOX or SUPER DIAMOND CLEAR VOX is highly recommended for use on this product.

---

## PRECAUTIONS/LIMITATIONS

- Store in a dry place.
- Mixing partial bags will give variable results; always mix full units.
- Minimum application temperature is 50 °F (10 °C).
- When necessary, follow the recommendations in ACI 305R “Guide to Hot Weather Concreting” or ACI 306R “Guide to Cold Weather Concreting”.
- Avoid applying material in direct sun.
- DO NOT use a solvent-based cure and seal on this product.
- DO NOT use plastic or other covering means to cure EUCO RE-COVER, for discoloration will occur.
- In all cases, consult the Safety Data Sheet before use

Rev. 09.22

---

**WARRANTY:** The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.