



EUCO[®] THX

POWDERED ADMIXTURE FOR HIGH STRENGTH NON-SHRINK GROUT

EUCLID CHEMICAL

PRODUCT INFORMATION

PACKAGING

Available in 25 lb (11.4 kg) pails

SHELF LIFE

6 months in original unopened container

SPECIFICATIONS/COMPLIANCES

ASTM C937

DESCRIPTION

EUCO THX is a powdered admixture which aids in the production of high strength, non-shrink grouts. It is ideally suited for grouting rock and soil anchors, micropiles, rockbolts and soil nails. High early strength grouts can be produced (5,000 psi) in 24 hours, allowing early stressing of anchors and loadings. High strength grouts are made using low water / cement ratio. EUCO THX increases grout flowability allowing them to be pumped and placed with ease. Additional components of EUCO THX provide expansion of the grout to compensate for typical shrinkage. EUCO THX contains no added chlorides or chemicals known to promote the corrosion of steel.

PRODUCT CHARACTERISTICS

FEATURES & BENEFITS

- Increases grout durability
- Reduces or eliminates grout shrinkage
- Enhances flowability of cement grouts
- Enables the development of higher strength at all ages
- Produces a thixotropic grout mix that reduces grout mobility once placed

PRIMARY APPLICATIONS

- Rock and Soil Anchors
- Micropiles, soil nails and rockbolts
- Where high strength, non-shrink grouts are required

PRECAUTIONS/LIMITATIONS

- Test mixes may be required due to variations in local materials and conditions
- Add to mix independent of other admixtures.
- In all cases, consult the Safety Data Sheet before use.

DIRECTIONS FOR USE

EUCO THX is generally dosed at rates ranging from 2 - 6 lb/100lb (2 - 6 kg/100 kg) of cementitious material. EUCO THX can be added to regular anchor grout mixes to improve flowability, increase grout strength and reduce grout shrinkage. To increase early and ultimate grout strength and further reduce or eliminate shrinkage, use 4 - 4 ½ gallons of water per 94 lbs of cement and 5 - 6 pounds of EUCO THX. Grout strength and shrinkage will vary depending on cement used.

Euclid Chemical recommends testing grout mixes prior to production. When casting sample cubes always use brass molds to provide confinement against expansion during curing. Because of variations in job conditions and concrete materials, dosages other than the recommended amounts may be required. In such cases, contact your local Euclid sales representative.

Rev. 04.21

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.