



EUCOPATCH

SINGLE-COMPONENT, RAPID-SETTING REPAIR MATERIAL

EUCLID CHEMICAL

PACKAGING

50 lb (22.7 kg) bag
Code: 065A 50
60 lb (27.2 kg) pail
Code: 065A 60

APPROXIMATE YIELD

50 lb (22.7 kg) unit: 0.44 ft³ (0.013 m³)
per unit when mixed with 0.7 to 0.75
gal (2.65 to 2.84 L) of potable water.

60 lb (27.2 kg) unit: 0.56 ft³ (0.016 m³)
per unit when mixed with 0.84 to 0.90
gal (3.2 to 3.4 L) of potable water.

MINIMUM/MAXIMUM APPLICATION THICKNESS

1/16 to 4 inches (1.6 mm to 102 mm)

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

2 years in original, unopened package

DESCRIPTION

EUCOPATCH is a single-component, rapid-setting, repair mortar for use on new and existing concrete and masonry surfaces. This product is designed for the reconstruction of damaged vertical and overhead concrete and masonry structures, both interior and exterior. EUCOPATCH can also be used in light-duty, pedestrian, horizontal applications. The light color of EUCOPATCH closely resembles aged, sun-bleached concrete.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Rapid-setting for repairs up to 4" (102 mm)
- High compressive strength
- Excellent resistance to freeze-thaw cycles and de-icing salts
- Suitable for both interior and exterior applications
- Light gray color blends well with aged concrete
- Compatible with galvanic anodes

PRIMARY APPLICATIONS

- Walls
- Curbs and gutters
- Precast panels
- Columns
- Overhead patching
- Masonry units

APPEARANCE

EUCOPATCH is a free-flowing powder designed to be mixed with water. After mixing and placing, the color may initially appear darker than the surrounding concrete. This color will lighten up substantially as the EUCOPATCH cures, resulting in the repair area very closely matching the surrounding concrete.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109	Compressive Strength	1 day 2,000 psi (14 MPa)
		7 days 4,500 psi (31 MPa)
		28 days 5,500 psi (38 MPa)
		56 days 6,500 psi (45 MPa)
ASTM C266	Set Times	Initial Set 8 minutes
		Final Set 20 minutes

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a minimum surface profile of CSP 5 - 7 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

Priming & Bonding (Saw Cut & Chipped Out Repairs): Thoroughly clean any exposed reinforcing steel, and apply DURALPREP A.C. to the concrete and the reinforcing steel within the repair area. Refer to the DURALPREP A.C. technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 to a dry substrate or a scrub coat of EUCOPATCH to the saturated surface dry (SSD) concrete surface may be used for bonding. The repair material must be placed on the scrub coat before the scrub coat dries out.

Priming & Bonding (Vertical & Overhead Skim Coats/Toppings): Apply EUCOWELD 2.0 to a dry substrate or a scrub coat of EUCOPATCH to the saturated surface dry (SSD) concrete surface. The repair material must be placed on the scrub coat before the scrub coat dries out.

Mixing: Single bags may be mixed with a drill and "jiffy" mixer. Use a paddle type mortar mixer for large jobs. All materials should be in the proper temperature range of 60 to 90 °F (16 to 32 °C). Add the appropriate amount of water for the batch size and then add the dry product. The mixed product should be quickly transported to the repair area and placed immediately.

Placement: Place EUCOPATCH onto the prepared concrete or masonry surface at a minimum depth of at least 1/16" (1.6 mm). Float or trowel flush with adjacent surface and allow to set. Finish to match the surrounding surfaces. Place EUCOPATCH while the scrub coat is still wet.

Finishing: Finish the repair material to the desired texture. Do not add additional water to the surface during the finishing operation. Use EUCOBAR evaporation retarder.

Curing and Sealing: Proper curing procedures are important to ensure the durability and quality of the repair. To prevent surface cracking, cure the material with a high solids curing compound, such as SUPER AQUA-CURE VOX or SUPER REZ-SEAL. Allow the curing compound to dry. In hot, windy or direct sunlight situations, apply a second coat of curing compound. If a curing compound is not desired, wet cure for a minimum of three days.

PRECAUTIONS/LIMITATIONS

- Only mix as much material that can be used in 10 minutes.
- Do not use for a topping or overlay.
- Do not use material at temperatures below 45 °F (7 °C).
- When necessary, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting" or ACI 306R "Guide to Cold Weather Concreting".
- Keep repair from freezing until a minimum strength of 1000 psi (7 MPa) is reached.
- Store product in a dry place.
- In all cases, consult the Safety Data Sheet before use.

Rev. 02.22

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.