

WATERPROOFING

Master Format #: 03 01 30.71

VANDEX PLUG

RAPID-SETTING, CRYSTALLINE HYDRAULIC CEMENT



EUCLID CHEMICAL

PACKAGING

50 lb (22.7 kg) pail
Code: V005P 05

APPROXIMATE YIELD

1 lb (0.45 kg) of VANDEX PLUG yields approximately 17 in³ (279 cm³) of repair material.

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

1 year in original, unopened package

DESCRIPTION

VANDEX PLUG is a rapid-setting hydraulic cement compound with crystalline properties used to instantly stop running water or seepage in masonry or concrete. VANDEX PLUG is ready to use and requires only the addition of water before plugging and sealing active leaks within a minute. Once VANDEX PLUG has set and stopped the flowing water, additional Vandex waterproofing treatments can be immediately applied over the top of it.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Initial set in 45 seconds
- Instantly stops running water or seepage leaks
- Positive or negative side application
- Can be applied underwater

PRIMARY APPLICATIONS

- Concrete pipe
- Foundations & basements
- Tunnels
- Dams & water reservoirs
- Manholes
- WTP & WWTP plants
- Culverts
- Spillways

APPEARANCE

VANDEX PLUG is a gray hydraulic cement compound.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109	Compressive Strength	1 hour 1,000 psi (6.9 MPa) 1 day 1,500 psi (10.3 MPa) 28 days 3,000 psi (20.7 MPa)
ASTM C348	Flexural Strength	7 days 300 psi (2.1 MPa) 28 days 350 psi (2.4 MPa)
ASTM C157	Expansion/Shrinkage 28 day length change	Moist Room (100% RH) 0.10% Dry Room (50% RH) -0.25%

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP > 3 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

Mixing: Pour potable water into a clean mixing container and gradually add VANDEX PLUG. Use approximately 1 quart of water to 8 to 9 lbs (3.8 to 4.3 kg/L) of material. Mix rapidly with a trowel to the consistency of stiff putty with no slump for no more than 20 seconds. VANDEX PLUG will flash set in 45 seconds. Properly mixed, VANDEX PLUG can be hand formed into a ball.

Application: Saturate, surface-dry (SSD) areas for repair with potable water immediately before application of VANDEX PLUG.

General Repairs: Force VANDEX PLUG into the crack or hole by hand or with a trowel. Rapidly fill to the full depth of the opening. **Patching Active Leaks:** Start at the top of the crack or hole, and force the VANDEX PLUG to the full depth of the prepared area. Apply direct pressure to the new patch until the VANDEX PLUG has taken a firm set. Mix fresh material, and continue patching toward the area of the greatest pressure. When extreme water pressure is encountered, physically hold the mixed VANDEX PLUG with a hand against the leak and apply continuous pressure until the VANDEX PLUG has set, and the water has stopped running. Do not use a twisting motion. **Floor-Wall Patching:** Follow above methods for the specific conditions encountered. Use a rounded tool to force the VANDEX PLUG into the joint, and construct a 45° transitional cove between the floor and wall at the same time. **Expansion/Contraction Cracks:** Do not use VANDEX PLUG to treat dynamic cracks. Consult the technical data sheets for the DURAL AQUA LINE of chemical/urethane grouts.

PRECAUTIONS/LIMITATIONS

- Do not apply VANDEX PLUG to frozen or frost filled surfaces.
- Do not twist VANDEX PLUG into the hole while plugging running water leaks.
- In warm weather, mix VANDEX PLUG with ice water. In cold weather, mix VANDEX PLUG with mildly warm water.
- Do not use in dynamic cracks or expansion joints. Use a chemical grout from the DURAL AQUA line.
- In all cases, consult the Safety Data Sheet before use.

Rev. 12.24

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.